

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C11D 3/22, D06M 15/11</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 98/23715</b> <b>(43) International Publication Date:</b> 4 June 1998 (04.06.98)
<b>(21) International Application Number:</b> PCT/US97/21841 <b>(22) International Filing Date:</b> 26 November 1997 (26.11.97)  <b>(30) Priority Data:</b> 60/031,960 27 November 1996 (27.11.96) US  <b>(71) Applicant (for all designated States except US):</b> THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> HUNTINGTON, Gregory, Bruce [US/BE]; Vergocienveld 7, B-3090 Overijse (BE). PRAMOD, Kakumanu [IN/US]; 7986 Kingfisher Lane, West Chester, OH 45069 (US). COLLINS, Royal, D. [US/US]; 126 St. Andrews, Cincinnati, OH 45245 (US).  <b>(74) Agents:</b> REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		<b>(81) Designated States:</b> BR, CA, JP, MX, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> RINSE-ADDED FABRIC CONDITIONING COMPOSITION BASED ON SPECIFIC STARCH AND METHOD USING SAME  <b>(57) Abstract</b>  A rinse-added fabric conditioning composition comprising a starch having a gelatinization temperature of less than 150 degrees C and a method for imparting crispness properties to fabrics treated with same.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

RINSE-ADDED FABRIC CONDITIONING COMPOSITION BASED ON SPECIFIC STARCH AND METHOD USING SAME

### Technical Field

This invention relates to compositions and methods for use during the rinse cycle of home laundering operations.

The compositions are especially effective for providing crispness and soil release benefits to fabrics.

### Background Art

Modern fabric conditioning compositions, washing machines and dryers are subject to continuous improvement with a view to achieve a series of fabric benefits such as, for example, softening, body, anti-wrinkling, ease of ironing, and improvement in appearance.

One prevalent laundry attribute that consumers desire is that fabrics maintain their original crisp look and feel, particularly those items which are routinely ironed.

Accordingly, it is an object of the present invention to provide a rinse-added fabric conditioning composition which impart crispness to fabrics rinsed therein.

It has now been found that the above objective is met by a rinse-added fabric conditioning composition containing starch. According to the present invention, the starch added in the rinse deposits uniformly on the fabric. This starch can then impart crispness to the fabric, particularly after exposure to heat (e.g., steam ironing, tumble drying).

It has also been found that the starching film provides resistance of the fabric to subsequent soiling and allows subsequent soils to be more easily removed. The removal in the subsequent wash can be done by chemical means (e.g., hydrolysis, amylase digestion) or physical mean (e.g., solvation, simple physical desorption and separation from the fabric).

Detergent compositions comprising starch are not new per se. Example is US 3,892,681 describing substantially water-insoluble starch. The starch is characterised by a granular diameter of 0.1-45 microns and a swelling power of less than 15 at 65°C improves the softness, the ease of ironing, the anti-static and anti-wrinkling performances. As of yet, however, no single fabric conditioning composition is available capable of providing textiles treated therewith in the conventional matter with the fabric-care benefits as referred to hereinabove.

#### Summary of the Invention

The present invention provides rinse-added fabric conditioning compositions which are capable of imparting crispness and soil release benefits to the fabrics.

These compositions comprise a specific starch having a gelatinization temperature of less than 150°C.

In a preferred embodiment, the compositions further contain, in addition to the specific starch, a perfume.

In its method aspect, the present invention relates to a method for treating fabrics to simultaneously impart crispness and improved subsequent cleaning benefits.

#### Detailed Description of the Invention

The rinse-added fabric conditioning compositions of the present invention comprise as an essential element a specific starch having a gelatinization temperature of less than 150°C.

The gelatinization temperature for gelatin is determined as setting point, several methods have been used to determine the setting point. Example is F.W. Wainwright, GGRA bull. 17(3), 10 (1966).

Although the final choice of starch which will meet requirements of this invention depends upon the origin of the material and also upon process conditions such as bleaching, degradation, and isolation applied to a given species, suitable starches can for example be selected from

- a. naturally occurring (e.g., corn, wheat, rice, tapioca, potatoes) or physically modified (e.g. small particle size such as rice starch or milled to promote smaller particle size and low temperature gelling; highly branched amylopectin content such as "waxy" starch grades; pre-gelatinized; acid treated).
- b. chemically modified (e.g. hydroxyalkyl substituted ethers, tertiary and quaternary aminoalkyl starch phosphates, starch acetates).

Preferred starches are starch compounds that are easy to formulate into a solid or liquid product; readily disperse in the final rinse; can be co-delivered with other ingredients such as perfumes; do not promote any adverse effects on fabrics (e.g. yellowing); and are readily strippable in the following wash.

Examples of preferred soluble modified and/or natural starches are waxy starches with PO (hydroxy propyl) groups, quaternary amine groups, a combination of PO and quats, high molecular cross linked and modified starches. Commercially available starch derivatives of this class are : Gelex ®, Polar gel® from American maize, Sta-lok® 180 and 374, Star-pol® 480 and 560 from Staley starch, Thermoflo®, National 1658 and Firm-tex from National starch.

The above mentioned benefit of crispness are obtained by the swelling and solvation of starch compounds at high temperature (50-75°C), gelatinization. These mechanisms result in the forming of a hydrophilic film that binds to the cellulose fibers of the fabric. The hydrophilic film retains the hydrophilic character of the fabric and the water vapor permeability.

The benefit of improved soil release removal is a result of the hydrophilic film serving as a protective soil release barrier (e.g., soil repellant, soil absorbent or adsorbent, surface modifier to aid detergency, etc.). During a subsequent wash, these films would be at least partially removed by detergents.

The starch can be added in the rinse as a dry powder or can be formulated and admixed as a cold water dispersion.

## Examples

### COMPOSITIONS

Two rinse-added fabric conditioning compositions (A/B) were prepared using Gelex® (A) and Polargel® (B). For each starch compound, a water dispersion was made (25 parts starch solids added to 75-175 parts water), heated to approximately 95+ °C with mixing to achieve a good dispersion, and then allowed to cool to ambient temperature.

### TREATMENT

For each starch conditioning product, representative cotton and polycotton fabrics were washed in a standard home laundering washing machine using a heavy duty detergent composition and median wash conditions. Part of this bundle was a set of white, 100% cotton woven fabric tracers. The starch conditioner was introduced into the final rinse cycle. A sufficient amount was added to deliver 25 grams of starch solids to the laundry load. Following laundering, the tracer swatches were line-dried, steam ironed, and then stained with a broad assortment of real stain materials that are commonly used for standard detergent performance assessment. After allowing the stain materials to dry, the swatches were then relaundered, without applying the starch conditioner in the final rinse. After line drying, these TEST swatches were then compared vs. a corresponding set of CONTROL swatches for the relative degree of stain removal, as judged by expert graders. The CONTROL swatches were prepared in an identical fashion to the TEST swatches, except no starch conditioner was applied in the final rinse during the first "pre-staining" laundering cycle.

### RESULTS

Positive and statistically significant (95% confidence level) stain removal benefits were observed for both starch materials across a broad spectrum of realistic stains. Results are expressed using the standard Panel Score Unit scale: +4 psu (very large difference in favor of TEST product) to -4 psu (very large difference in favor of CONTROL product).

Gelex® Treatment A		Polargel® Treatment B	
Stain	Results	Stain	Results
cooked butter	+ 1.8 s	cooked butter	+ 2.3 s
curry blend sauce	+ 1.2 s	dirty motor oil	+ 2.6 s
wine	+ 2.1 s	lipstick	+ 1.2 s
red currant	+ 0.6 s	ketchup	+ 1.7 s
chocolate pudding	+ 2.4 s	wine	+ 1.0 s
milk chocolate	+ 1.7 s	milk chocolate	+ 1.2 s
grass	+ 0.6 s	clay - type A	+ 1.4 s
clay - type A	+ 2.5 s	clay - type B	+ 0.8 s
clay - type B	+ 2.2 s		
clay - type C	+ 1.4 s		
clay - type D	+ 2.4 s		

In addition to the above soil release benefits, it was also observed that a starch conditioning treatment delivered in the claimed manner (final rinse) could impart a noticeably different and more crisp feel versus the nonconditioned swatches.




What is claimed is:

1. A rinse-added fabric conditioning composition comprising a starch having a gelatinization temperature of less than about 150°C.
2. A method for treating fabrics to impart crispiness properties to the fabrics by treating fabrics in an aqueous solution comprising the composition as defined in claim 1.

## INTERNATIONAL SEARCH REPORT

 International application No.  
PCT/US97/21841

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC(6) : C11D 3/22, D06M 15/11 US CL : 510/474, 521, 522 According to International Patent Classification (IPC) or to both national classification and IPC																				
<b>B. FIELDS SEARCHED</b> Minimum documentation searched (classification system followed by classification symbols) U.S. : 252/FOR 239; 510/474, 521, 522 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)																				
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>																				
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.																		
X	US 4,162,983 A (JOHNSON) 31 July 1979 (31-07-79), column 2, lines 20-39; column 2, line 59 - column 3, line 5; column 7, lines 47-52; Examples I, IV & VII.	1-2																		
X	US 4,178,254 A (LEIKHIM ET AL) 11 December 1979 (11-12-79), abstract; column 1, lines 47-59; column 5, lines 20-35; column 9, lines 56-61; Examples I & VI.	1-2																		
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.																				
<table border="0"> <tr> <td>* Special categories of cited documents:</td> <td>*T</td> <td>later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</td> </tr> <tr> <td>*A* document defining the general state of the art which is not considered to be of particular relevance</td> <td>*X*</td> <td>document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</td> </tr> <tr> <td>*E* earlier document published on or after the international filing date</td> <td>*Y*</td> <td>document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</td> </tr> <tr> <td>*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</td> <td>*g*</td> <td>document member of the same patent family</td> </tr> <tr> <td>*O* document referring to an oral disclosure, use, exhibition or other means</td> <td></td> <td></td> </tr> <tr> <td>*P* document published prior to the international filing date but later than the priority date claimed</td> <td></td> <td></td> </tr> </table>			* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	*A* document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	*E* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*g*	document member of the same patent family	*O* document referring to an oral disclosure, use, exhibition or other means			*P* document published prior to the international filing date but later than the priority date claimed		
* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention																		
*A* document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone																		
*E* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art																		
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*g*	document member of the same patent family																		
*O* document referring to an oral disclosure, use, exhibition or other means																				
*P* document published prior to the international filing date but later than the priority date claimed																				
Date of the actual completion of the international search 20 JANUARY 1998		Date of mailing of the international search report <b>25 FEB 1998</b>																		
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230		Authorized officer  ARDITH HERTZOG Telephone No. (703) 308-0661																		